



Clay paint

Technical data sheet

5l / Item no.066602401 / EAN 4007955666127

10l / Item no.066603401 / EAN 4007955666134



Warm white interior paint for walls and ceilings on mineral substrates (such as clay, gypsum, lime and cement plaster, masonry and concrete), woodchip wallpaper, mineral-based paint fleece, firmly adhering and absorbent emulsion and mineral paint finishes, plasterboard and gypsum fibreboard, and similar substrates. It helps to regulate the moisture content of the indoor air, thereby promoting a comfortable indoor climate.

- good coverage
- moisture-regulating and breathable
- Easy to apply with a roller or brush
- vapour-permeable
- solvent-free and plasticiser-free
- free from ingredients of animal origin
- Contrast ratio: H₁₀ Class 2 with a coverage of 7 m²/l
- Wet abrasion resistance: Class R 4 in accordance with DIN EN 13300
- Gloss level: G3 matt
- Max. grain size: S1 fine

Area of application

Warm white interior paint for walls and ceilings. Moisture-regulating, ideal for use on mineral substrates, woodchip wallpaper and plasterboard.

Preparation

The substrate must be dry, clean and sound. Remove any old paint that is not firmly adhering, distemper and loose plaster. Pre-treat highly absorbent, sandy and chalky surfaces with proMineral primer.

Processing

Stir the clay paint thoroughly before use and apply it with a brush, roller or a suitable spray gun. Apply two coats if necessary. The first coat may be thinned with a maximum of 10 per cent water. The top coat should be applied undiluted once the first coat has dried thoroughly. Do not apply when the substrate or room temperature is below +5 °C. Clean tools with water immediately after use.

Tinting:

For coloured finishes, the clay paint can be tinted with a maximum of 4 per cent universal tinting concentrates (LW-Oxyd types only) or with proMineral coloured paints.

Drying time:

Under normal conditions (20 °C, 65% relative humidity, moderately absorbent substrate), the drying time is approx. 6–12 hours. Under unfavourable conditions (e.g. low temperature or high humidity), the drying time may be extended.

Consumption

1 litre is sufficient for approx. 6–8 m² with a single coat – depending on the condition of the substrate. Determine the exact amount required by carrying out a test application on the surface.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.

Storage

Store containers tightly sealed in a cool place, but away from frost. Do not allow the product to enter the sewer system, watercourses or the ground. Only send completely empty containers for recycling. Dried-out residues can be disposed of with household waste or as construction site waste.

Notes

Keep out of the reach of children. Due to the high pH value, avoid contact with the eyes and skin. It is recommended that you wear gloves and safety goggles (not glass). In case of skin contact, rinse thoroughly with plenty of water. In case of eye contact, rinse immediately with plenty of water and seek medical advice if necessary.

Please refer to the safety data sheet for safety-related information. Up-to-date safety data sheets are available on our website www.pro-mineral.com.

EU VOC limit value for this product (Cat.: A/a, Wb) = 30 g/l (2010). Maximum VOC content of this product: 0.5 g/l.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.